



E-TUFF® 80 Heavy Duty Base & Intermediate Coat Parking and Walking Deck Membrane

Single Component, Water Catalyzed, Solvent and TDI Free Base Membrane for Metal, Wood, Concrete Surfaces

1.01 DESCRIPTION

E-Tuff® 80 is a single-component, water-catalyzed, fast-setting, rapid-curing, solvent-free, TDI free, based on patented technology. This high-performance, and high-solids polyurea/urethane polymer produces a waterproof base membrane that can be applied to suitably for heavy-duty wearing surface applications on prepared interior or exterior, concrete, plywood, and metal surfaces. Due to its fast gel time, E-Tuff® 80 is suitable for applications in temperatures as low as 20°F (-6.6 °C). It may be applied in a single or multiple applications. E-Tuff® 80 is also relatively insensitive to moisture and temperature allowing applications in various temperatures and humidity. Be sure to use the right product grade that complies with VOC regulations as per federal, state, statutory bodies, county and city regulations/codes at the place of installation of product.

1.02 FEATURES

- Green concrete
- Seamless
- Non gassing
- Fast curing
- No odor
- Excellent low temperature flexibility
- Good thermal stability
- May be applied at any thickness in one pass
- Meets the Criteria of ASTM C-836 & E-96
- Highly flexible over extreme temperatures
- Excellent weathering
- Labor saving
- User friendly
- Resists dirt attraction
- Recoatable

1.03 TYPICAL USES

- Heavy Duty Vehicular Parking Decks
- Mechanical Room
- Portico Waterproofing
- Sloping and coving
- Exterior and Interior Waterproofing Traffic Areas
- Flooring
- Walkways, Patio's and Stairways
- Basketball Courts
- Sun Rooms
- Pre-cast Joints
- Metal Roofs
- Block and Masonry
- Resurfacing

1.04 COLORS

White or Grey. Custom colors are available upon request with minimum order quantity.

1.05 PACKAGING

1-gallon kit: One 1 gallon (3.78 liters) can
5-gallon kit: One 5 gallon (18.9 liters) pail

TECHNICAL DATA

(Based on draw down film).

Solids by Weight	93 ±2%
Solids by Volume	90 ±2%
Viscosity @75°F (24°C)	2500-3500 cps
Pot Life min @75°F (24°C) 50%	15-20 minutes
Tack Free Time	3-4 hours
Hardness ASTM D-2240 Shore A	80 ± 3
Tensile Strength, ASTM D-412	1500 ± 300 psi (10.34 ± 0.7 MPa)
Elongation, ASTM D-412	400 ± 100%
Tear, ASTM D-624	175± 25pli (30.7 ± 4 kN/m)
Volatile Organic Compounds, ASTM D-2369-07	0.64 lbs/gal 77 gm/liter
Specific Gravity	1.08 ± 0.1

1.06 SURFACE PREPARATION

Refer to General and Safety Guidelines for complete information. Concrete surfaces require a medium sandpaper finish equal to or greater than an ICRI CSP #3. Surface preparation may be completed by shot blasting or the use of Poly-Tuff Profile and Etch Cleaner. Peel and adhesion tests are recommended.

Install a 100-200 sqft (9.30-18.58 sqm) mock-up of the system to be installed and approve for aesthetics, color, texture, actual coverage rates and functionality before proceeding.

1.07 MIXING

- A. Before application, premix E-Tuff® 80 using a mechanical mixer (Jiffy mixer) at slow speed or if mixing by hand mix at least for 5 minutes or until a homogeneous mixture and color is obtained. Use care not to allow the entrapment of air into the mixture.
- B. Optional: Add catalyst (one vial per 5 gallon or 18.9 liters pail) and mix thoroughly until a homogeneous mixture and color is obtained. Catalyst will reduce cure time for cold temperature applications. Depending upon environmental conditions up to 3 vial of catalyst per 5 gallons (18.9 liters) may be used.
- C. Mix pre-accelerated E-Tuff 80 with water at a volume ratio of 4:1 (4 gallons or 15.4 liters of E-Tuff® 80 with 1 gallon or 3.78 liter of water). For 5 gallons or 18.9 liters of E-Tuff® 80 add 1.25 gallon or 4.725 liters of water. Mix the material thoroughly until water is completely combined with E-Tuff® 80. Water catalyzed material is referred as mixed or water catalyzed material.

1.08 JOINTS, CRACKS, AND FLASHING

Joints and Cracks over 1/16 inch (0.16 cm) shall be sealed flushed with E-101 and taped before applying basecoat (See Super Seal Tape Technical Data Sheet). Prime all concrete and metal joints, cracks, and flashings with recommended PSI Primer. Note: Primer is optional over new plywood.

Where polyester tape is used, firmly embed the tape into the pre-stripe of basecoat with a trowel. Applying a thin coat of E-Tuff® 80 paste over the reinforced tape and smooth onto adjacent surface.

The use of Flexi-Flashing is acceptable in most applications for replacing metal flashing except at door pockets.

APPLICATION

2.01 APPLICATION BASICS

For best results use a squeegee or notched trowel. Airless sprayer or phenolic-resin-core roller may be used but extra care should be taken not to trap air which may result in bubbles.

Spread E-Tuff® 80 mixture evenly over the entire deck. Application should not be stopped part way across an area. Each application should be done in one complete step. A continuous application will ensure a smooth and level coat with no lines or streaks to disfigure the deck coating.

When E-Tuff® 80 mixed material begins to gel, approximately 15 minutes after placement, broadcast 14-30 mesh rubber granules into the wet membrane to refusal. Normal usage is 20 lbs of rubber granules p/100 sqft (0.98 kg/m²).

When broadcasting silica sand, allow membrane to thicken to a firm and sticky surface (approximately 30-45 min) when the sand will adhere but not sink into the base coat. The aggregate should be dry, washed, and rounded silica in the, 12-20, 16-30 or 20-40 mesh size and a 6.5 Moh's scale minimum hardness as required by customer

specifications or as specified in the system specifications. The time needed for thickening to a firm sticky condition is dependent on atmospheric environments especially temperature and humidity. Allow coating to cure 2-4 hours before proceeding to subsequent coats. E-Tuff® 80 may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil (25.4 microns) thickness is one gallon per 1440 sqft (134 sqm). Refer to individual Systems Description under System Specifications Section of the Poly-Tuff Systems International (PSI) catalog or website for specific coverage rates.

Coverage rates and cure times will vary depending on temperature, relative humidity, surface roughness, porosity, aggregate selection, embedment, and application technique. Coverage rates provided are optimal and are not guaranteed.

2.02 EQUIPMENT CLEANUP

E-Tuff® 80 typically skins over within 45 minutes and cures throughly in 4 to 7 hours depending upon temperature, humidity and thickness. Lower temperatures and humidity prolong cure time. Higher temperatures accelerate cure time. Equipment should be cleaned with an environmentally safe solvent, as permitted under local regulations, immediately after use.

2.03 STORAGE

E-Tuff® 80 has a shelf life of twelve (12) months from date of manufacture when stored indoors at a temperature between 60°F to 95°F (15-35°C) in original, factory-sealed containers.

2.04 LIMITATIONS

- E-Tuff® 80 should be used only as a base membrane. The components of E-Tuff® 80 are not UV stable and are not designed to withstand direct wear/abrasion without aggregate and topcoat.
- Ensure that the substrate is properly prepared prior to application. Surfaces to be coated with E-Tuff® 80 must be dry, clean, free of foreign matter, and primed with recommended PSI Primer. Primer is optional over new plywood.
- PSI recommends that an aggregate of washed, dry, rounded, crystal silica sand, 16-30 mesh (0.595-1.19 mm), with 6.5+ Mohs minimum hardness or EPDM rubber granules 14-30 mesh (0.595-1.41 mm) size be used to aid in slip resistance. Applicator should determine mesh size based on job requirements. Whenever rubber aggregates are used, two coats of topcoat are required to sufficiently provide a wearing surface.
- Any remaining material must be tightly sealed to protect it against curing in its container. Containers that have been opened must be used within 1 or 2 weeks since E-Tuff® 80 is a moisture reactive material that begins to cure when exposed to air.
- PSI does not recommend that E-Tuff® 80 be diluted with solvents.
- For complete information associated with the application of E-Tuff® 100, refer to individual System Specifications and Guidelines.



TECHNICAL DATA SHEET

SECTION 3.2.1

The following conditions must not be coated with PSI deck coating systems:

1. On grade or below grade slabs
2. Split slabs with buried membrane
3. Sandwich slabs with insulation
4. Slabs over unvented metal pans
5. Suspended pool decks & swimming pools
6. Magnesite and light weight concrete
7. Asphalt surfaces and asphalt overlays

WARNING: This product contains isocyanates.

Please read all information in the General & Safety Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. PSI Products are for "Professional Use Only" and preferably applied by professionals who have prior experience with the PSI Products or have undergone training in application of PSI Products. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data, instructions, and project specific recommendations.

LIMITED WARRANTY

PSI warrants its products to be free of manufacturing defects and that they will meet PSI current published physical properties. PSI warrants that its products, when properly installed by a state licensed waterproofing contractor according to PSI guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of 12 months. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by PSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. PSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. PSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. PSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.