



2250 E. Tropicana Ave Phone: (866) 977-8833  
 Suite 19-600 Fax: (800) 804-0182  
 Las Vegas, NV 89119 Email: sales@polytuffus.com  
 Web: www.polytuffus.com

## SPECIFICATION

**FLEXIDECK® P-MD**

*60 Dry Mills Water Curable  
 Fast Cure Coating System for  
 Ship & Metal Deck Surfaces*

**SYSTEM DESCRIPTION**

**1.01 Flexideck® System P-MD is liquid fluid applied, skid resistant, water resistant, polyurethane, pedestrian traffic system for maritime decks and other metal surfaces.**

**A.** The system utilizes a primer, one coat of a Water Induced Urethane (WIU)<sup>™</sup> basecoat and two coats of urethane topcoat. Flexideck® P-MD can be applied to protect surfaces against corrosion damage and chemicals commonly encountered on these surfaces. It is an elastomeric system designed to expand and contract with normal structural movements. Flexideck® P-MD is a proven waterproofing system. Installed and maintained properly, Flexideck® P-MD decking system will ensure years of service.

**1.02 FEATURES**

- ❖ Seamless
- ❖ Elastomeric
- ❖ Fast-Curing
- ❖ Recoatable
- ❖ Good Weatherability
- ❖ For use in California excluding SCAQMD areas, use Topshield® EST (CAL)
- ❖ For use in SCAQMD areas, use Enviro-Grip® EP#2(SC), P-Tuff® Classic or Flex, Topshield® EST(SC), Topshield® ALP-150(SC), Staintuff® 3072(SC)

**1.03 TYPICAL USES**

- ❖ Shipboard Walkways/Stairs
- ❖ Over Occupied Space
- ❖ Mechanical Rooms

**1.04 PRODUCT INSTRUCTIONS**

**A.** For complete information asso-

ciated with the application of Flexideck® P-MD, refer to the general guidelines section of the PSI catalog which describes the surface preparation, job conditions, finishing details and other necessary information.

**B.** All products/materials to be used on this system should be purchased from Poly-Tuff Systems International (PSI) or its distributors or approved by PSI. For details on individual product, please refer to Product Technical Data Sheet.

**APPLICATION****2.01 Inspection**

**A.** Check area of application to ensure that it conforms to the substrate requirements, as stated in the general guidelines section.

**2.02 Priming**

**A.** Prime surface with Enviro-Grip® EP#1 or EP#2 at a rate of 1 gallon (mixture of Part-A & Part-B) per 300 sq. ft. (0.14 liters/m<sup>2</sup>). Apply using a brush or phenolic core roller. This will result in minimum 3 dry mils (76 microns) of coating.

**B.** Allow Primers to become thumbprint tacky before proceeding to Coating Application. The point at which the primer is generally discerned as nearly tack free is when the primer passes the thumbprint test. The thumbprint test is defined by when a thumbprint is left in the primer and the primer does not transfer onto the thumb. If the primer has been allowed to remain tack free for more than 12 hours, it is necessary to solvent wipe the primed area and re-prime.

**2.03 Coating Application**

**A.** P-Tuff® mixed material is a mix-

ture of 4 parts P-Tuff® Classic and 1 part of water by volume. Apply mixed P-Tuff® Classic to substrate at a rate of 3 gallons/100 sq. ft. (1.2 liters/m<sup>2</sup>). Application will require more or less material depending on substrate conditions.

**B.** Use a notched trowel or squeegee to spread P-Tuff® Classic mixed material evenly over the entire deck resulting in a min. 42 ± 2 dry mils (1066 ± 50 microns) thick membrane.

**C.** When P-Tuff® Classic mixed material begins to gel, broadcast 14-30 mesh rubber granules until refusal. The amount of rubber used will vary. (Normal usage is 20 lbs rubber granules/100 sq. ft.)

**D.** When P-Tuff® Classic mixed material is firm enough to support the weight of the installer without damaging the material, or when coating is dry (approximately 2-3 hours), remove all loose aggregate, preferably by vacuum. Make any touch-up or repairs. Allow repairs to cure.

**2.04 Top Coat Application**

**A.** Apply desired color of Topshield® EST topcoat at a rate of 1gallons/100 sq. ft. (0.4 liters/m<sup>2</sup>). This coat will result in an additional 10 ± 2 dry mils (254 ± 50 microns) thick coating.

**B.** At 70°F and 50% relative humidity allow a minimum of 16 and a maximum of 48 hours for topcoat to cure.

**C.** Apply second coat of Topshield® EST at a rate of ¾ gallons/100 sq. ft. (0.31 liters/m<sup>2</sup>). This coat will result in an additional 8 ± 2 dry mils (203 ± 50 microns) thick coating.

#### **D. OPTIONAL FAST CURE**

Topcoat: The addition of Topshield® Accelerator will shorten cure time to 6 to 8 hours for each coat.

#### **E. OPTIONAL TOPCOATS**

Topshield® EST may be substituted with:

- 1) Chem-Sentry® II for chemical resistance
- 2) Topshield® ALP-150 for value engineered projects
- 3) Staintuff® 3072 for fast cure

#### **2.05 FINISHED SYSTEM**

**A.** When applied as directed above, Flexideck® P-MD decking system will provide min. 60 ± 5 dry mils (1524 ± 100 dry microns), exclusive of aggregate, of superior waterproofing protection.

#### **2.06 LIMITATIONS**

**A.** Uncured materials are sensitive to heat and moisture.

**B.** Proper coating application techniques should ensure a deck with no lines or streaks.

**C.** The substrate must be sloped for proper drainage.

**D.** PSI assumes no liability for substrate defects.

#### **2.07 Job Completion**

**A.** Equipment should be cleaned with an urethane grade environmentally safe solvent, as permitted under local regulations, immediately after use.

**B.** Field visits by PSI personnel are for the purpose of making technical recommendations only and are not to supervise or provide quality control on the job site.

**WARNING: The products in this system contain Isocyanates, Solvent, Epoxy Resin and Curatives.**

---

Please read all information in the general guidelines, product data sheets, system specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data and instructions.

#### **DISCLAIMER**

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.