



2250 E. Tropicana Ave Phone: (866) 977-8833
 Suite 19-600 Fax: (800) 804-0182
 Las Vegas, NV 89119 Email: sales@polytuffus.com
 Web: www.polytuffus.com

P-TUFF® SEALANT 8001

*100% Solids Thixotropic
 Polyurethane Polyurea Caulking Compound*

DESCRIPTION

P-Tuff® Sealant 8001 is a two component aromatic, 1:1 ratio, rapid setting, thixotropic, 100% solids, polyurethane polyurea caulking compound for bonding application.

FEATURES

- ❖ 100% Solids Meets VOC Regulations
- ❖ Sandable in 20-30 minutes
- ❖ Odorless
- ❖ Meets USDA Criteria
- ❖ Non-Toxic
- ❖ Non-Sag in Vertical Application
- ❖ Meets California VOC and SCAQMD Requirements

USES

P-Tuff® Sealant 8001 is used as bonding agent for plastics, masonry, wood, polyurethane EPS and other surfaces.

- ❖ Automobile Bumper Repair
- ❖ EPS Blocks
- ❖ Plastic Repair

Note: P-Tuff® Sealant 8001 will discolor in exterior applications.

COLORS

Side-A Black, Side-B Clear

PACKAGING

10 gallon kit: One 5 gallon pail of Side-A and one 5 gallon pail of Side-B.

100 gallon kit: One 55 gallon drum (net 50 gallons) of Side-A and 55 gallon drum (net 50 gallons) of Side-B.

APPLICATION

For best results machine dispense using a 1:1 ratio pump, with or without heater as required.

This material can be applied at temperatures from 32°F (0°C) to as high as 135°F (57°C).

The product needs to be conditioned at 75-80°F prior to use.

TECHNICAL DATA

Specific Gravity	
Part-A	1.18
Part-B	1.01
Gel Time @ 75°F, ASTM D-2471	90-120 seconds
Tack Free Time @ 75°F	5-7 mins
Sandable Time @ 75°F	20-30 mins

FINISHING

Allow P-Tuff® Sealant 8001 to cure for 20-30 minutes before sanding.

CLEANUP

Cured product may be disposed of without restriction. Mix excess A and B material and allow to cure. Check local, state and federal laws before disposing of material.

STORAGE

P-Tuff® Sealant 8001 should be stored at 60-90°F (15-35°C).

P-Tuff® Sealant 8001 has a shelf life of one (1) year from date of manufacture in original, factory sealed containers.

LIMITATIONS

Discoloration will occur if exposed to UV, however no change will occur in the physical properties.

WARNING

This product contains Isocyanates and Curatives.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data and instructions.

LIMITED WARRANTY

PSI warrants its products to be free of manufacturing defects and that they will meet PSI current published physical properties. PSI warrants that its products, when properly installed by a state licensed waterproofing contractor according to PSI guide specifications and product data sheets over a sound, properly prepared substrate, will not allow water migration for a period of 12 months. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by PSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. PSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. PSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. PSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the users responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.