



P-TUFF® SEALANT PG (PTS PG)

A Two Component, Pourable Grade, 100% Solids Polyurethane

1.01 DESCRIPTION

P-Tuff® Sealant PG is a self leveling, two component, 1:5 (1A:5B) ratio by volume, pourable grade, 100% solids polyurethane joint sealant. Please use the correct product grade that complies with VOC regulations as per federal, state, county and city regulations/codes at the place of installation of product.

1.02 FEATURES

- 100% Solids Meets VOC Regulations
- Cured Material Remains Flexible, Even In Cold Temperatures
- Flexible
- Odorless

1.03 TYPICAL USES

P-Tuff® Sealant PG is used on interior and exterior horizontal concrete surfaces to repair random cracks and control joints.

- Airports
- Bridge Headers
- Grade Matching
- Industrial/Manufacturing Facilities
- Parking Garage Decks
- Saw/Utility Cuts
- Spalls
- Truck Aprons

1.04 COLOR

Concrete Grey

1.05 PACKAGING

1.5-gallon kit: 1 quart can (0.95 liters) of Side-A and 2 gallon pail, net fill 1.25 gallons (4.73 liters) of Side-B.

1.06 SURFACE PREPARATION

- Allow concrete to cure 28 days before installation.
- All joints must be clean and dry prior to installing P-Tuff® Sealant PG.
- If joint is damp, dry with heat torch.
- Remove all dust from the concrete pores prior to installing P-Tuff® Sealant PG.
- Backer rod should be used in control joints to control the sealant depth. The depth of the sealant should be 1/2 the width of the joint not to exceed 2" (5.08 cm) and no less than 4" (10.16 cm).
- Construction joints are to be filled to full depth using no backer rod or silica sand.
- To repair T-joints, the joint should be cut a minimum of 25% of the total depth of the slab. The side of the T-joint must be cut 1-1/2" (3.81 cm) from the joint and a minimum of 1/2" (1.27 cm) deep.
- For random crack and spall repairs each side of the crack should be

TECHNICAL DATA (Based on draw down films)

Specific Gravity	A-Side: 1.02 ± 0.1 B-Side: 1.44 ± 0.1
Viscosity at 80°F (26°C)	A-Side: 65 ± 10 cps B-Side: 70 ± 10 cps
Mixing Ratio (A:B) by Volume	1:1 (1A:1B)
Pot Life @ 77°F (25°C) 50% RH	30-40 minutes
Tack-Free Time @ 77°F (25°C) 50% RH	12 Hours
Cure Time @ 75°F (24°F), RH 50%	36-48 Hours
Hardness, ASTM D-2240 Shore A	30 ± 5
Tensile Strength, ASTM D-412	300 ± 50 psi (2.1 ± 0.3 MPa)
Tear Strength, ASTM D-624	50 ± 5 pli (8.8 ± 0.8 kN/m)
Elongation, ASTM D-412	800 ± 50%
Total Solids by weight and volume	100%

- cut to create a minimum 1/2" (1.27 cm) deep vertical edge. Ensure that all joint edges are at 90° angles to grade with no V-grooving or feather edges.
- All surfaces must be primed with Enviro-Grip™ EP#2 or Enviro-Grip™ EBF-LV.

1.07 MIXING

P-Tuff® Sealant PG may not be diluted under any circumstance.

Pre-mix P-Tuff® Sealant PG Side-B material before combining with Side-A. Note: Side-A material requires no mixing. Add Side-A to Side-B while mixing, using a mechanical mixer with a low speed drill and "Jiffy" Mixer blade. Mix until a homogeneous mixture and color is obtained (at least 5 minutes).

Use care to scrape the sides of the container to ensure that no unmixed material remains. Use caution not to whip too much air into the material as this may result in pinhole blisters or shortened pot life.

APPLICATION

2.01 APPLICATION BASICS

Apply using a caulking gun, hand pressure-type or pour from container. This material can be applied at environmental temperatures from 40°F (4.4°C) to as high as 135°F (57° C). The product needs to be conditioned

at 75-80°F (24-26°C) prior to use.

2.02 FINISHING

After applying P-Tuff® Sealant PG wait 36-48 hours, depending on temperature and humidity before open to traffic.

2.03 CLEAN-UP

Cured product may be disposed of without restriction. Mix excess Side-A and Side-B material and allow to cure. Check local, state and federal laws before disposing of material.

2.04 SHELF LIFE AND STORAGE

P-Tuff® Sealant PG has a shelf life of 12 months from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

2.06 LIMITATIONS

- Do not use in cracks, construction joints or control joints if surface is subject to thermal cycling.
- Discoloration will occur if exposed to UV, however no change will occur in the physical properties.

WARNING: This product contains isocyanates and curatives.

Coverage Rates - Linear Feet / Gallon

		Width of Joint						
		1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"
depth of Joint	1/4"	308	205	154	123	102	88	77
	3/8"	205	136	102	82	68	58	51
	1/2"	154	102	77	61	51	44	38
	5/8"	123	82	61	49	41	35	30
	3/4"	102	68	51	41	34	29	25
	7/8"	88	58	44	36	29	25	22
	1"	77	51	38	30	25	22	19

Coverages and yields shown do not include allowances for loss or waste and variations in job conditions. Each user must establish his own factors for loss from experience.

Please read all information in the General & Safety Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. PSI Products are for "Professional Use Only" and preferably applied by professionals who have prior experience with PSI Products or have undergone training in application of PSI Products. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data, instructions, and project specific recommendations.

LIMITED WARRANTY

PSI warrants its products to be free of manufacturing defects and that they will meet PSI current published physical and chemical properties. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by PSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. PSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. PSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. PSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.