



P-TUFF® SEALANT CR-SF (PTS CR-SF)

A Two Component, 70 Shore D, Concrete Repair Product and Fissure/Crack Filler

1.01 DESCRIPTION

P-Tuff® Sealant CR-SF is a two component, low odor, liquid applied, polyurethane system designed to repair concrete and masonry substrates. The new surface will protect concrete from weather, corrosion, erosion, freeze/thaw spalling and chemical attack. Please use the correct product grade that complies with VOC regulations as per federal, state, county and city regulations/codes at the place of installation of product.

1.02 FEATURES

- Waterproof
- Excellent Abrasion Resistance
- Repairs Can Be Made in Hot or Cold Weather
- Rapid Cure Allows Traffic to Resume in 30 Minutes

1.03 TYPICAL USES

- Hairline Cracks
- Pavement Divots
- Thin, Wide or Deep Cracks
- Concrete Highway & Pothole Repair

1.04 COLOR

Side-A: yellow, Side-B: blue

1.05 PACKAGING

2-gallon kit: 1 gallon (3.78 liters) can Side-A, 1 gallon (3.78 liters) can Side-B

10-gallon kit: 5 gallon (18.9 liters) pail of Side-A and 5 gallon (18.9 liters) pail of Side-B

1.06 SURFACE PREPARATION

Hairline Crack Repair: Blow out the cracks with dry compressed air to remove loose and unsound material.

Large Crack Repair: Remove loose and unsound material in the crack by blowing the cracks with dry compressed air. Fill the cracks with sand that is at least 12 mesh or larger.

APPLICATION

2.01 APPLICATION BASICS

P-Tuff® Sealant CR-SF should be applied using a proportioning dispensing system.

This type of system transfers, meters, and mixes the co-reactive Side-A and Side-B components at a very high rate and at the required proportions. The machine transfers from 1 gallon (3.78 liters) or 5 gallon (18.9 liters) containers through proportioning pumps at the specified ratio of 1:1. Both components are pumped through a disposable static mixing tube. The combined mixture can then be dispensed onto the gravel or sand prepared crack.

Material left in the static mixing tube will thicken in approximately 1 minute and solidify in 3 minutes. Static mixing tube should then be

TECHNICAL DATA (Based on draw down films)

| | |
|-----------------------------------|--|
| Specific Gravity | A-Side: 1.10 ± 0.1 B-Side: 0.95 ± 0.1 |
| Viscosity at 75°F (26°C) | A-Side: 20 ± 5 cps B-Side: 20 ± 5 cps |
| Mixing Ratio (A:B) by Volume | 1:1 (A:B) |
| Pot Life @ 77°F (25°C) 50% RH | 240-300 seconds |
| Gel Time @ 75°F (24°C), 50% RH | 50-70 seconds |
| Flash Point | >150°F (>65.6°C) |
| Hardness, ASTM D-2240 Shore A | 70 ± 5 |
| Tensile Strength, ASTM D-412 | 4000 ± 400 psi (28 ± 0.3 mPa) |
| Compressive Strength**, ASTM C-42 | 4750 ± 400 psi (32.76 ± 2.7 kN/m) |
| Elongation, ASTM D-412 | 7 ± 0.50% |
| Bond Strength to Concrete | Excellent |
| Thermal Compatibility to Concrete | Good |

**Compressive strength was checked on composite of silica sand (12 mesh, 6.5 Moh's minimum hardness) and 18 to 20% of P-Tuff® CR in a 4" x 8" cylinder (10.14 cm x 20.18 cm).

discarded.

2.02 FINISHING

P-Tuff® Sealant CR-SF is a rapid cure material that will be completely cured in approximately 5-10 minutes. P-Tuff® Sealant CR-SF is very sensitive to heat and moisture. Higher temperatures and/or high humidity will accelerate the cure time. Low temperature and/or low humidity may slightly extend the cure time.

2.03 CLEAN-UP

Equipment should be cleaned immediately after use with an environmentally safe solvent, as permitted under local regulations.

2.04 CHEMICAL RESISTANCE

P-Tuff® Sealant CR-SF was unaffected by the following chemicals (Based on ASTM D-814):

Acidic Chemicals

Acetic Acid, 1%
Acetic Acid, 10%
Hydrochloric Acid, 1%
Hydrochloric Acid, 10%
Sulfuric Acid, 1%
Sulfuric Acid, 10%

Basic Chemicals

Ammonium Hydroxide, 1%
Ammonium Hydroxide, 10%
Oils, Fuels and Other Chemicals
Hydraulic Oil
Motor Oil
Unleaded Gas (Regular)
Unleaded Gas (Premium)
Hexane
IPA MIBK
Xylene

2.05 SHELF LIFE AND STORAGE

P-Tuff® Sealant CR-SF has a shelf life of 12 months from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C).

2.06 LIMITATIONS

- Surfaces must be dry, clean and free of foreign matter.
- Should be used in well-ventilated areas due to its strong odor.
- Containers that have been opened must be used as soon as possible.
- Do not dilute under any circumstance.
- P-Tuff® Sealant CR-SF is for concrete crack repairs only. Slippery when wet.
- Refer to General and Safety Guidelines for more information.

WARNING: This product contains isocyanates and solvent.

Please read all information in the General & Safety Guidelines, Technical Data Sheets, Guide Specifications and Safety Data Sheets (SDS) before applying material. PSI Products are for "Professional Use Only" and preferably applied by professionals who have prior experience with PSI Products or have undergone training in application of PSI Products. Published technical data and instructions are subject to change without notice. Contact your local PSI representative or visit our website for current technical data, instructions, and project specific recommendations.

LIMITED WARRANTY

PSI warrants its products to be free of manufacturing defects and that they will meet PSI current published physical and chemical properties. Seller's sole responsibility shall be to replace that portion of the product which proves to be defective. There are no other warranties by PSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. PSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. PSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. PSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and PSI makes no claim that these tests or any other tests, accurately represent all environments.